



Quality Products Since 1932 • DRYLOK® • ZAR® • UGL®

## **Spray Specifications D-99**

### **DRYLOK® Floor & Wall Masonry Waterproofer**

For best results **DRYLOK® Floor & Wall Masonry Waterproofer** should be well stirred and sprayed at room temperature (70°F and 60% relative humidity). Conditions of high humidity and/or low temperature can cause poor results. It is recommended that a small test area be done before beginning the project.

Spray Recommendation:

Gas Powered Option: GMAX II 5900 or Larger

- Standard (Hi-Boy – P/N 248688/ Lo-Boy P/N 248687)
- Premium (Hi-Boy – P/N 258732/ Lo-Boy P/N 258737)

Electric Powered Option: Ultra Max II 1596 or larger

- Standard Hi-Boy P/N 258764
- Premium Hi-Boy P/N 2578763

Spray this material with a tip size of .031-.035 tip.

Spray cross hatching patterns with two coats building to a 14 to 16 wet mil thickness.

Revised April 3, 2019

---

**570-344-1202 • 1-800-845-5227 • Fax 570-969-7634 • [www.UGL.com](http://www.UGL.com)**

Corporate Office: 1396 Jefferson Avenue, Dunmore, PA 18509 • Mail to: P.O. Box 70, Scranton, PA 18501-0070  
Plant Locations: Jacksonville, IL • Jackson, MS